



Warren Paint and Color Co.

700 Wedgewood Avenue (at I-65)
Nashville, Tennessee 37203
www.warrenpaint.com
Phone: 615-292-6655 / Fax: 615-292-6654
Emergency: 800-535-5053

Prepared: April 1, 2009

Product Data Sheet

1250
Vinyl Acrylic
Exterior Flat Latex House Paint

Quality, Weather Resistant Finish
Blister and Mildew Resistant
Available in Many Colors

Vinyl Acrylic is a high quality exterior flat latex paint that produces a one coat finish on most repaint work. Due to its excellent hide and film build, fewer coats are needed over new or unpainted surfaces. *Vinyl Acrylic* is easily applied and provides an ordinary life expectancy of five years.

Surface Preparation:	Remove all dirt, grease, and loose, peeling paint. Sand previously painted surfaces for best adhesion. For best results, prime with the appropriate Warren primer. Use <i>Insured Oil House Primer</i> to prime wood and surfaces previously painted with oil-based enamel. <i>Super Block Filler</i> is best for unpainted concrete block and rough concrete. Use a <i>Metalcoat</i> primer over steel or aluminum. Allow adequate dry time before finishing with <i>Vinyl Acrylic</i> . Self-priming is possible over concrete, brick, and concrete block.
Mixing and Thinning:	Stir or shake well. Thin sparingly with water to spray. Do not over-thin.
Application:	Brush, roll, spray. Thin as directed. Apply between 50 and 90°F with the relative humidity less than 80%. Cover objects in the vicinity of painting to avoid paint drips or spatters.
Dry Time:	One hour to touch. Two hours to handle. 24 hours hard
Recoat Time:	After four hours.
Appearance:	Velvet-flat white finish.
Pigmentation:	Rutile titanium dioxide, calcium carbonate, mica, and zinc oxide.
Vehicle:	Vinyl acrylic copolymer emulsion.
% Solids by Weight:	51.5
% Solids by Volume:	34.3
Coverage:	393 square feet per gallon at 1.4 mils DFT (100% transfer and zero profile). Realistically 75-150 square feet per gallon over extremely rough surfaces. Approximately 400 square feet per gallon is possible over previously primed or painted smooth surfaces.
V.O.C.:	0.37 lb/gal (44 g/l) with water; 0.95 lb/gal (114 g/l) without water.
Cured Film Properties:	Tough, flexible film with good dirt pick up resistance and good exterior durability.
Standard Packaging:	One gallon cans. Fives and drums are available by special order.